


MI Cable Thermocouple Assemblies



Style MTA1 — Transition to Lead Wire (Stock)



Ordering a Stock MTA1 Thermocouple

(Thermocouples not available from stock can be custom manufactured—see page 14-15)


TEMPCO stocks **MTA1 style Thermocouples** in type J and K in the standard lengths listed in the following two tables. These thermocouples have Teflon[®] insulated leads with a 2-1/2" split lead termination. Order a stock unit from the tables after completing the ordering code with

the Junction Type Code from Box 5 and Optional Compression Fitting Code from Box 6 below.

Type J – 316 SS Sheath

		"L" Dimension			
Diame	ter 6"	12"	18"	24"	
0.063	ST1-JD06B	ST1-JD12B	ST1-JD18B	ST1-JD24B	
0.125	ST1-JF06B	ST1-JF12B	ST1-JF18B	ST1-JF24B	
0.250	" ST1-JH06B	ST1-JH12B	ST1-JH18B	ST1-JH24B	

"L" Dimension 12" 24" Diameter 6" 18" 0.063" ST1-KD06B ST1-KD12B ST1-KD18B ST1-KD24B ST1-KF12B ST1-KF18B ST1-KF24B 0.125" ST1-KF06B ST1-KH06B ST1-KH12B ST1-KH18B ST1-KH24B 0.250"



MARNING: Cancer and Reproductive Harm - www.P65Warnings.ca.gov.

Type K – Alloy 600 Sheath


View Product Inventory @ www.tempco.com

Temperature Sensing



MI Cable Thermocouple Assemblies

Style MTA1 — Transition to Lead Wire (Custom Manufactured)



Temperature Sensing

MI Cable Thermocouple Assemblies



MI Cable Thermocouple Assemblies

Mineral Insulated Metal-Sheathed Cable

Thermocouple Assemblies are made from TEMPCO's high quality Tempco-Pak and will incorporate all the same outstanding features.

Important Features:

- *★ Accurate*
- * High Temperature Rating
- ***** Fast Response
- * Moisture Proof
- * Thermal Shock Resistant
- **∗** Can Be Formed
- **∗** Weldable
- ***** High Pressure Rated
- ***** Compact
- ***** Durable

Typical Applications

- •• Bearing Temperature
- Diesel Engines
- ➡ Food Processing
- •• Furnaces
- Glass Manufacturing
- Heat Treating
- ➡ Kilns
- Metal Processing
- •• Oil Processing
- •• Ovens
- Petrochemicals
- Power Stations
- ➡ Refineries
- Research Laboratories
- Steam Generators
- ➡ Turbines

(Hot or Measuring Junctions available on single or dual element cable)

Hot Junctions ••

Choose the measuring junction that best suits your particular needs:

Exposed Junction (E)

Thermocouple wires are butt-welded. Insulation is sealed against liquid or gas penetration prior to use.

This junction style provides the fastest possible response time but leaves the thermocouple wires unprotected against corrosive or mechanical damage.



Grounded Junction (G)

The sheath and thermocouple wires are welded together, forming a completely sealed integral junction. Recommended in presence of liquids, moisture, gas or high pressure. The wire is protected from corrosive or erosive conditions. In the Grounded Junction, response time approaches that of the Exposed Junction.



Ungrounded Junction (U)

Thermocouple junction is fully insulated from welded sheath end. Excellent for applications where stray emf's would affect the reading and for frequent or rapid temperature cycling. With the Ungrounded Junction, response time is slightly longer than for the Grounded Junction.

Temperature Sensing



MI Cable Thermocouple Assemblies

Selecting the Correct Tempco-Pak Thermocouple Assembly

Thermocouples must be selected to meet the conditions of each particular application. The environment, operating temperature and atmosphere, response time and length of service must be considered when selecting the sheath, insulation, calibration, junction and termination of the thermocouple assembly.

Sheath Materials

The most commonly used sheath materials and their maximum continuous operating temperatures in an oxidizing atmosphere are as follows:

Sheath Material	Max. Operating Temperature
Alloy 600	2150°F (1177°C)
304 Stainless Steel	1650°F (899°C)
316 Stainless Steel	1650°F (899°C)
310 Stainless Steel	2100°F (1150°C)



Note: For temperatures exceeding 2200°F (1204°C), Noble or Refractory metal sheaths are normally used.

Calibrations

The table shows the standard temperature ranges for the various ANSI thermocouple calibrations:

ANSI Letter	Thermocouple Type	Temperat °F	ure Range (°C)
J	Iron-Constantan	32-1400	(0-760)
Κ	CHROMEL P®-ALUMEL®	32-2300	(0-1260)
Ν	Nicrosil-Nisil	32-2300	(0-1260)
Т	Copper-Constantan	32-660	(0-350)
Е	CHROMEL P®-Constantan	32-1600	(0-871)
R	Pt 13% Rhodium-Platinum	32-2700	(0-1482)
S	Pt 10% Rhodium-Platinum	32-2700	(0-1482)
В	Pt 30% Rh-Pt 6% Rh	1600-3100	(871-1704)

Refer to the Mineral Insulated Thermocouples and Cable section regarding sheath, insulation and calibration (pages 14-114 through 14-118).

TEMPCO's engineering staff will be happy to assist you with the design and selection of your thermocouple requirements.

Formability

Because Tempco-Pak is fully annealed it can normally be formed around a mandrel 4 times the sheath diameter. Consult TEMPCO if special forming is required.

Weldability

The thermocouple sheath can be brazed, soldered or welded. Welding the thermocouple sheath in the field is not recommended on diameters less than .093 in. All welding should be done in an inert atmosphere.

Assembly Tolerances: Sheath Length Dimensions

Sheath O.D.	"L" Tolerance Up to 24"	"L" Tolerance Over 24"
Up to .038"	±1/2"	±2%
.038" to .065"	$\pm \frac{3}{8}''$	$\pm 1\frac{1}{2}\%$
Larger than .06	$5" \pm \frac{1}{4}"$	±1%

Flexible Lead Dimensions

Lead Length (ft.)	Tolerance	
Up to 5	+6", -1"	
5 to 10	+6", -2"	
over 10	+5%, -2%	

(800) 323-6859 • Email: sales@tempco.com